

TITLE: 2241 Initial Evaluation of the Multibar Sawless Lint Cleaner

DISCIPLINE: Engineering and Ginning

AUTHORS: Greg Holt (Corresponding Author)
USDA-ARS Cotton Production and Processing Research Unit
1604 E. FM 1294
Lubbock, TX 79403
Phone: (806) 746-5353
Email: gholt@lbr.ars.usda.gov

Roy Baker (Retired)
USDA-ARS Cotton Production and Processing Research Unit
1604 E. FM 1294
Lubbock, TX 79403

Ed Barnes
Cotton Incorporated
6399 Weston Parkway
Cary, NC 27513

DISCLAIMER:

ACKNOWLEDGEMENTS: Mention of product or trade names does not constitute an endorsement by the USDA-ARS over other comparable products. Products or trade names are listed for reference only.

ABBREVIATIONS: The partial support of this research by Cotton Incorporated is gratefully acknowledged.

Initial Evaluation of the Multibar Sawless Lint Cleaner

ABSTRACT

Experiments were conducted to evaluate the performance of a prototype lint cleaner named the Multibar Sawless Lint Cleaner (MBSLC). The MBSLC was conceived as a possible replacement for the first stage of lint cleaning in a cotton gin. The MBSLC has similarities to a saw-type lint cleaner, but the saws have been replaced with a spiked-tooth cylinder and a much denser series of grid bars are used. The theory of replacing the first stage was based on inefficiencies seen in a conventional two saw-type lint cleaner operation where the first stage of lint cleaning experiences the heaviest loading of trash and does a majority of the cleaning. The second stage is less efficient since it is both operationally and mechanically redundant to the first stage of lint cleaning. The MBSLC was designed under the premise that more effective and efficient cleaning of the lint would occur if different mechanical principles of operation were used in series rather than the traditional saw-type lint cleaner followed by a saw-type lint cleaner.

This initial study was performed on a single variety of upland cotton that was stripper harvested with a field cleaner. The MBSLC was compared to a conventional saw-type lint cleaner by evaluating the fiber quality and lint waste produced by each machine. Results showed the MBSLC produced 73% less lint cleaner waste than the conventional saw-type lint cleaner. The MBSLC had improved fiber properties of length, short fiber content, and trash size. Fiber properties of Rd and leaf grade were better from the saw-type lint cleaner. All other measured fiber properties were the same for both lint cleaners. The results emphasized the potential application of this technology to improve lint cleaning, possibly by use as a stage of “pre-cleaning” before a saw-type lint cleaner, or even as a sole stage of cleaning for lint with low leaf levels. Additional studies are being planned to evaluate other spike designs and operating parameters of the MBSLC.

KEYWORDS

Lint Cleaner, Cotton, Ginning, Lint, Fiber Quality

INTRODUCTION

Controlled-batt saw-type lint cleaners are the most common means of cleaning lint for cotton gins processing mechanically harvested upland cotton (Columbus, 1985; Mangialardi, 1995). The use of lint cleaners has a significant impact on the value and quality of ginned lint (Baker, 1978). However, a balance exists between too much cleaning and not enough. Too little or too much cleaning of cotton can lower the value of the lint in the marketplace and create processing problems at the textile mill (Lalor and Baker, 1985; Bel et. al., 1991; Mangialardi, 1996; Baker and Brashears, 1999). Finding the correct balance between over or under cleaning the lint is both an art and skill developed by an experienced ginner based on the condition of the incoming seed cotton. In past studies, one of the main issues evaluated was the number of stages of lint cleaning. Griffin et. al. (1982) evaluated the effects of fiber damage and spinning qualities with up to six-stages of lint cleaning. Mangialardi (1993) conducted a four-year study of spindle-harvested cotton to determine the effect that various stages of lint cleaning had on fiber quality and market value. Baker and Brashears (1999) compared bale values of stripper harvested cotton based on zero to three stages of lint cleaning over a 5-year period. A commonality seen in those three studies was that increasing the number of stages of lint cleaning resulted in increased fiber damage, lint waste, and neps. The benefits gained by increasing the stages of lint cleaning (i.e. reducing the trash content) did not necessarily result in greater bale values (\$). Even though one stage of lint cleaning may be sufficient for some cotton, two stages of lint cleaning are still needed for other types of cotton which have higher trash levels.

When multiple stages of saw-type lint cleaners are operated in series, Mangialardi (1993) showed that the cleaning efficiency of each lint cleaner decreased significantly as the number of stages increased. Thus, this research was initiated to develop and evaluate an alternative lint cleaner. This lint cleaner could act as a first stage of cleaning by removing some of the foreign matter from the lint without adversely effecting fiber quality while producing less lint waste than the traditional saw-type lint cleaner. The prototype alternative lint cleaner was named the Multibar Sawless Lint Cleaner (MBSLC). For the initial evaluation, the objectives were to: 1) compare fiber quality, lint waste, and production data of the MBSLC to a conventional saw-type lint cleaner and 2) if the results showed a promising potential for the MBSLC, initiate plans for future studies evaluating other settings and configurations involving multiple varieties.

MATERIALS AND METHODS

Equipment

The MBSLC (Fig 1) was constructed and installed behind the number one gin stand at the USDA-ARS, Cotton Production and Processing Research Unit in Lubbock, Texas. The MBSLC was constructed using a standard Hardwick-Etter lint condenser, feed works from a Continental 16D lint cleaner, a specially manufactured spiked cleaning cylinder (Fig 2), and twenty-two adjustable grid bars. The inside width of the lint condenser and MBSLC is 154.9-cm (61-in) and 167.6-cm (66-in), respectively. The MBSLC cleaning cylinder consisted of pins that were 3.2 mm (0.125 in) in diameter and 4.1 cm (1.625 in) long. The cylinder contained 0.2 pins/cm² (1.3 pins/in²).

Setup, Testing, and Data Collection

The cotton variety used in this study was FiberMax 960BR. The seed cotton was stripper harvested with a field cleaner and moduled and stored in a dry area. Moisture content of the seed cotton was determined by Shepard (1972). The average moisture content, at the feeder apron, was 5.9% wet basis with a standard deviation of 0.15%, thus the seed cotton did not require the use of heat/drying during ginning.

The machinery sequence for all pre-cleaning and ginning of the seed cotton was the same; steady flow, cylinder cleaner, extractor, cylinder cleaner, extractor, feeder, and Continental Double Eagle 93-saw gin stand. The lint from the gin stand passed through either the standard Horn and Gladdin 66 (HG-66) saw-type lint cleaner or the MBSLC and then to the press. The ginning rate and combing ratio for the HG-66 test runs was 7.3 bales/h and 27:1, respectively. For the MBSLC test runs, the ginning rate was 7.4 bales/h and the combing ratio of the lint cleaner was 30:1. Each test run consisted of approximately 454 kg (1000 lb) of seed cotton.

The data recorded for each run consisted of: 1) time, 2) ambient temperature, 3) relative humidity, 4) weight of seed cotton used, 5) cleaning time, 6) gin time, 7) lint weight, 8) seed weight, and 9) mote weight. During each run, one seed cotton and three lint samples were collected. Lint samples were obtained before and after the lint cleaner for fiber quality analysis with the Advanced Fiber Information System (AFIS) and High Volume Instrument (HVI) fiber measurement systems (Uster Technologies, Knoxville, TN). The HVI analyses took place at the USDA-AMS Classing Office in Lubbock, TX and at Cotton Incorporated's facility in Cary, North Carolina. The AFIS analyses were done at Cotton Incorporated's facility. Seed cotton samples were collected for moisture analysis (Shepard, 1972) from the feeder apron. Lint cleaner waste was collected for fractionation and usable fiber content by the Shirley Analyzer (ASTM, 1996).

Experimental Design and Data Analysis

This study was a completely randomized design with two treatments, standard saw-type lint cleaner and MBSLC. Each treatment was replicated six times. Standard analysis of variance techniques were used to determine the statistical significance among the two treatments using Tukey's Honestly Significant Difference (HSD) test (release 9.1.3; SAS Institute Inc.; Cary, NC). The response variables evaluated from the data included: 1) Turnout, 2) Lint Cleaner Waste, 3) Loan Value, 4) AFIS data, and 5) HVI data.

RESULTS & DISCUSSION

Table 1 shows the observed significance level for comparisons of the standard lint cleaner to the MBSLC for the process response variables evaluated. The data shows the MBSLC to have higher turnout ($P = 0.035$) and less lint cleaner waste ($P < 0.001$) than the standard lint cleaner. The waste from the standard lint cleaner contained 26.9% fiber equating to 0.626 kg/bale (1.38 lb/bale). Lint cleaner waste from the MBSLC contained 25.3% fiber equating to 0.161 kg/bale (0.354 lb/bale). Even though more usable lint was removed from the standard lint cleaner, the improvement in grade by the removal of foreign matter resulted in a higher loan value [\$1.247/kg (\$0.5653/lb)] than the lint from the MBSLC [\$1.214/kg (\$0.5505/lb)]. Table 1 shows the bale weight to be higher ($P = 0.035$) for the MBSLC, which corresponds to the higher turnout obtained. The loan bale value shown in Table 1 was calculated by multiplying the loan value by the bale weight and was shown to be relatively the same for both lint cleaners. The similarity in bale loan value may seem surprising considering the lint from the saw-type lint cleaner had a higher loan value. However, the MBSLC had a higher bale weight which offset

the higher loan value of the saw-type lint. Ginning rate for both treatments was shown to be the same ($P = 0.855$).

Table 2 shows the observed significance level for the AFIS and HVI fiber quality data used as response variables. The AFIS fiber quality data shows the MBSLC to have longer length ($P = 0.019$ by weight and $P = 0.014$ by number), less short fiber ($P = 0.014$ by weight and $P = 0.026$ by number), fewer neps ($P = 0.004$), and smaller size trash ($P = 0.002$). The data also shows trash ($P = 0.002$), Dust ($P < 0.001$), and Visible Foreign Matter ($P < 0.001$) for the MBSLC to be higher than for the standard saw-type lint cleaner. The HVI data showed Upper Half Mean length ($P = 0.001$) to be longer for the MBSLC. The standard lint cleaner had higher Rd ($P = 0.009$) and +b ($P = 0.005$) values than the MBSLC. The standard lint cleaner had lower leaf grade ($P < 0.001$) than the MBSLC. The leaf grade in Table 2 has decimals because the reported values are the average of six runs. It should be noted that the seed cotton used in this study was field cleaned cotton that graded Strict Low Middling on color from samples collected prior to lint cleaning. Differences in fiber quality may be more/less evident when other varieties are evaluated with differing trash levels.

The fiber quality and production results from the spiked cylinder of the MBSLC were different than those reported by Columbus (1989) and Le (2006). Both Columbus and Le reported shorter fiber length, higher short fiber content, and more neps from the spiked/pinned cylinders evaluated in their studies. Also, in Le's study he found the pinned cylinder to have lower turnout and produced more waste than the saw-type lint cleaner. The MBSLC performed almost exactly the opposite than the spiked/pinned cylinder in Columbus and Le. The pinned cylinder used in Le's study was one of the two evaluated in Columbus' study with the inclusion of additional speeds, varieties, and combing ratios. Possible explanations as to the differences seen in the two previous spiked/pinned cylinder studies and this one may be attributed to the differences in the spiked cylinders, the number of grid bars, and/or the scale of lint cleaner. The two cylinders evaluated by Columbus' study had 6.5 pins/cm^2 (42 pins/in^2) and 0.77 pins/cm^2 (5 pins/in^2) compared to the 0.2 pins/cm^2 (1.3 pins/in^2) of the MBSLC. In addition to differences in spike/pin density, Columbus' cylinders had a maximum length of 1.9-cm (0.75-in) compared to 4.1 cm (1.625 in) of the MBSLC. The number of grid bars in the lint cleaner used in the previous studies contained five grid bars compared to the twenty-two adjustable grid bars of the MBSLC. The differences that could result from the scale of the lint cleaners (i.e. 38.1-cm [15-in] width versus 167.6-cm (66-in) width) would more than likely relate to throughput, 4.8 bales/h versus 7.4 bales/h for the MBSLC.

Future Studies

Based on the results from the initial study, future studies are being developed to broaden the evaluation of the MBSLC to include: 1) other pin configurations and densities, 2) various commonly grown upland cotton varieties, and 3) various operating speeds and combing ratios. The pin patterns to be evaluated in upcoming studies are shown in Fig 3. The lags (i.e. metal slats that contain the pins) shown in Fig 3 are going to be bolted in place around the cylinder as shown in Fig 4. Fig 4 shows the cylinder with Lag Set 3. The lag sets shown in Fig 3 vary in pin density, angle of the pin extending from the lag, and pattern around the cylinder. Pin densities of the new lag sets range from 0.68 pins/cm^2 (4.4 pins/in^2) to 0.2 pins/cm^2 (1.3 pins/in^2).

SUMMARY AND CONCLUSIONS

A prototype sawless lint cleaner named the Multibar Sawless Lint Cleaner (MBSLC) was developed and tested at the USDA-ARS, Cotton Production and Processing Research Unit's gin lab in Lubbock, Texas. The initial evaluation consisted of ginning one variety of cotton and comparing turnout, fiber properties, and lint cleaner waste to a conventional saw-type lint cleaner. The results indicate the MBSLC to have longer length, less short fiber content, fewer neps and a higher turnout than the saw-type lint cleaner. However, the MBSLC had higher foreign matter, more leaf, and lower Rd than the conventional lint cleaner. The less aggressive nature of the MBSLC appears to be beneficial for retaining length and reducing neps but results in more foreign matter being left in the lint. Overall, the MBSLC has promise as a first stage of lint cleaning or a stand alone lint cleaner. Working as the first stage of a two stage lint cleaning operation, the MBSLC may allow a second stage saw-type lint cleaner to do a better job of combing and cleaning the cotton than two stages of saw-type lint cleaning. As a stand alone lint cleaner that replaces saw-type lint cleaning, the MBSLC needs to do a better job of removing foreign matter without adversely effecting fiber properties. Additional studies are needed to validate the findings reported in this study using more cotton varieties with varying trash levels. Future studies will focus on evaluating various pin patterns, pin densities, and operational settings.

REFERENCES

- ASTM. 1996. Standard test method for non-lint content of cotton - designation D2812-88. W. Conshohocken, Pa.: Am. Soc. for Testing and Materials.
- Baker, R.V. 1978. Performance characteristics of saw-type lint cleaners. *Trans ASAE*, Vol. 21(6): 1081-1091.
- Baker, R.V. and A.D. Brashears. 1999. Effects of multiple lint cleaning on the value and quality of stripper harvested cotton. *In Proc. Beltwide Cotton Conf.*, 1391-1393. National Cotton Council, Memphis TN.
- Bel, P.D., E. P. Columbus, C.K. Bragg, and K.Q. Robert. 1991. Effects of mechanical cleaning on cotton fibers part I: ginning. *Tex. Res. J.*, Vol. 61(2): 83-88.
- Columbus, E.P. 1985. Effect of lint cleaner saw speed and tooth density on cotton quality. *Trans ASAE*, Vol. 28(5): 1692-1696.
- Columbus, E.P. 1989. Pinned cylinders in lint cleaners. *In Proc. Beltwide Cotton Conf.*, 646-649. National Cotton Council, Memphis TN.
- Griffin, A.C., G. J. Mangialardi, Jr., and J. D. Barger. 1982. Six-stage lint cleaning: effect on fiber and spinning quality parameters. *In Proc. Beltwide Cotton Conf.*, 164-167. National Cotton Council, Memphis TN.
- Lalor, W.F. and R.V. Baker. 1985. Performance of conventional and new lint cleaners. *Trans ASAE*, Vol. 28(2): 610-616.
- Le, Sanh. 2006. Performance of a pin cylinder lint cleaner. *In Proc. Beltwide Cotton Conf.*, 651-657. National Cotton Council, Memphis TN.
- Mangialardi, G.J., Jr. 1993. Effect of lint cleaning at gins on market value and quality. *Trans ASAE*, Vol. 9(4): 365-371.
- Mangialardi, G.J., Jr. 1995. Alternate carding and combing procedures for cotton lint cleaners. *Trans ASAE*, Vol. 11(6): 801-810.
- Mangialardi, G.J., Jr. 1996. Lint cleaning options to preserve fiber quality at gins. *Trans ASAE*, Vol. 12(5): 555-562.
- Shepard, J.V. 1972. Method of oven drying seed cotton. *In Standard Procedures for Foreign Matter and Moisture Analytical Tests Used in Cotton Ginning Research*. USDA-ARS, Agricultural Handbook No. 422. 13 pp.

TABLES

Table 1. Process data comparisons between a standard saw-type lint cleaner and the multibar sawless lint cleaner.

| Response Variable | Unit | Standard Lint Cleaner | Multibar Sawless Lint Cleaner | Observed Significance Level |
|------------------------------|---------------|-----------------------|-------------------------------|-----------------------------|
| Turnout | % | 28.4 | 29.2 | 0.035 |
| Lint Cleaner Waste | % | 1.03 | 0.28 | <0.001 |
| Gin Rate | bales/h | 7.29 | 7.38 | 0.855 |
| Loan Value ^z | \$/kg (\$/lb) | 1.247 (0.5653) | 1.214 (0.5505) | 0.006 |
| Bale Weight | kg (lb) | 219.11 (483.05) | 225.45 (497.04) | 0.035 |
| Loan Bale Value ^y | \$/bale | 273.23 | 273.69 | -- |

(z) 2005-06 CCC loan rates for Lubbock, TX.

(y) Loan Bale Value = Loan Value * Bale Weight. The value shown in the table is based on the metric units. Differences between the reported units and those obtained with the English units are due to rounding errors associated with conversion from metric.

Table 2. Fiber quality data comparisons between a standard saw-type lint cleaner and the multibar sawless lint cleaner.

| Response Variable ^z | Unit | Standard Lint Cleaner | Multibar Sawless Lint Cleaner | Observed Significance Level |
|-----------------------------------|---------|-----------------------|-------------------------------|-----------------------------|
| Advanced Fiber Information System | | | | |
| Length (w) | cm (in) | 2.240 (0.882) | 2.278 (0.897) | 0.019 |
| UQL | cm (in) | 2.885 (1.136) | 2.911 (1.146) | 0.113 |
| SFC (w) | % | 16.88 | 15.73 | 0.014 |
| Length (n) | cm (in) | 1.589 (0.626) | 1.635 (0.644) | 0.014 |
| SFC (n) | % | 42.69 | 40.89 | 0.026 |
| Trash Size | um | 335.7 | 316.1 | 0.002 |
| Dust | cnt/g | 290.1 | 434.2 | <0.001 |
| Trash | cnt/g | 62.5 | 80.4 | 0.002 |
| VFM | % | 1.18 | 1.62 | <0.001 |
| SCN Size | um | 1123 | 1124 | 0.956 |
| SCN | cnt/g | 20.5 | 20.3 | 0.918 |
| Neps | cnt/g | 401 | 352 | 0.004 |
| High Volume Instrument | | | | |
| UHM | cm (in) | 2.822 (1.111) | 2.855 (1.124) | 0.001 |
| UI | % | 80.33 | 80.64 | 0.057 |
| Rd | | 78.56 | 77.57 | 0.009 |
| +b | | 8.58 | 8.26 | 0.005 |
| Leaf Grade | | 2.9 | 3.7 | <0.001 |

(z) Length = length by weight (w) and by number (n), UQL = Upper Quartile Length, SFC = Short Fiber Content by weight (w) and by number (n), VFM = Visible Foreign Matter, SCN = Seed Coat Neps, UHM = Upper Half Mean, UI = Uniformity Index, Rd = reflectance, +b = yellowness. The value reported for Leaf Grade is the average of six runs which is why the value has a decimal.

FIGURES

Figure 1. Schematic cutaway view of the multibar sawless lint cleaner




Figure 2. Close-up three-dimensional view of the spiked cylinder used in this study




Figure 3. Side-view and top-view of the eight lag sets to be evaluated in future studies of the multibar sawless lint cleaner




Figure 4. Close-up three dimensional view of lag set 3 on the cylinder in the multibar sawless lint cleaner

